

TEST REPORT

Report No. : PN:TR:1354009142

DATE : 27/07/2022



CARZSPA AUTOFRESH PRIVATE LIMITED

204, SIDDHI VINAYAK PLATINUM, OPP D.MART ON VIP ROAD, NEAR KAILASHNAGAR
SURAT-394220

IN

CONTACT PERSON : ANCKUR SAMA

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION CRYSTALSHIELD TRINITY 9H

OEM OTHER

COUNTRY OF ORIGIN INDIA

SAMPLE RECD ON 21/07/2022

TESTING PERIOD : 25/07/2022 – 26/07/2022

TEST(S) REQUESTED PENCIL HARDNESS

PENCIL HARDNESS TEST:

JIS K 5600 Part 5 Section 4 : 1999 / As specified by client

Test condition : Sample pre-conditioned at 23±2°C and 50±5% RH for 16 hrs.
Test conducted at 23±2°C and 50±5% RH.

Pencil type : Mitsubishi UNI pencil.
Pencil holding angle : 45°±1°
Pencil load : 750±10 gm
Speed : 0.5 -1 mm/s

Grading scale : 6B · 5B · 4B · 3B · 2B · B · HB · F · H · 2H · 3H · 4H · 5H · 6H · 7H · 8H · 9H · 10H
Softer ← → Harder

No. of Sample(s) : 02



Requirement : 9 H

Observation :

Sample No.	Hardness	Visual observation
1	9H	No scratches observed up to 9H.
2	9H	No scratches observed up to 9H.



Test photographs :





Conclusion : Tested sample meet's the requirement.

Note : Test performed as per the conditions given by the client.

***** End of Report*****

Per pro SGS India Private Ltd.

Bhushan Tambe
Executive

Email your Test Report Related Enquiries at Feedback.trp@sgs.com